



SHANGRAO RUICHEN SEALING CO.,LTD
DONGGUAN RUICHEN SEALING CO.,LTD

Address: Road 8.Yanshan Industrial Estate, Shangrao City, 334500, Jiangxi Prov., CHINA
 Tel: +86-18024335478 E-mail: aaron@dgork.com

MATERIALS TEST REPORT

FKM75 BLUE FDA-A401C (V7502F-A401C) COMPOUND

ASTM D2000 M2HK 757 A1-10 B38 EO78 EF31 F13

Press Cure		Post Cure		
Sheet : 10min 170°C		Sheet : 16 hrs 230°C		
Button : 10 min 170°C		Button : 16 hrs 230°C		
ORIGINAL PROPERTIES	SPECIFICATION	TEST RESULT	ASTM TEST METHOD	
HARDNESS SHORE A	75±5	73	D2240	
TENSILE STRENGTH, MPA, MIN	≥7	10.61	D412	
ULTIMATE ELONGATION, %, MIN	≥150	176.23	D412	
SPECIFIC GRAVITY (g/cm ³)		2.00	D297	
HEAT RESISTANCE 70 H . AT 250°C (A1-10)			D573	
CHANGE IN HARDNESS, POINTS	+10	+2		
CHANGE IN TENSILES STRENGTH, %	-25	+7.26		
CHANGE IN ULTIMATE ELONGATION,MAX %	-25	-10.93		
COMPRESSION SET, MAX, 22H AT 200°C (B38)	≤30	19.15	D395	
FLUID RESISTANCE FUEL.101. 70H AT 200°C (EO78)			D471	
CHANGE IN HARDNESS, POINTS	-15~+5	-8		
CHANGE IN TENSILES STRENGTH, MAX %	-40	-21.5		
CHANGE IN ULTIMATE ELONGATION,MAX %	-20	-12.3		
CHANGE IN VOLUME %	0~+15	+8.62		
FLUID RESISTANCE FUEL C, 70H AT 23°C (EF31)			D471	
CHANGE IN HARDNESS, POINTS	±5	-3		
CHANGE IN TENSILES STRENGTH, MAX %	-25	-15.62		
CHANGE IN ULTIMATE ELONGATION,MAX %	-20	-12.6		
CHANGE IN VOLUME %	0~+10	+5.2		
LOW-TEMPERATURE BRITTLNESS NONBRITTLE				
AFTER 3MIN AT -10°C (F13)	NONBRITTLE	PASS	D2137	

Remark:

- The data are based on testing slabs I buttons and are for reference purpose only..
- Our compound can meet above -mentioned ASTM 2000 Spec.
- This information is, to the best of our knowledge, accurate reliable to the date indicated.
- The above mentioned data have been obtained by tests we consider as reliable, We don't assure that
 - the same results can be obtained other laboratories, using different conditions by the preparation and
 -evaluation of the samples.

Approved By	Frankie Fang	Checked By:	Yunli Tu	Tested By:	Jianjun Zhu
-------------	--------------	-------------	----------	------------	-------------